

## Tecta

Barrier Dispersion Coated Folding Box Board



Grammage g/m <sup>2</sup>	Thickness µm	Stiffness, Taber (mN/m)	
		MD	CD
230	320	11,0	4,8
245	350	13,0	5,5
265	400	16,5	7,0
290	450	22,0	9,5
315	500	26,0	11,0
345	550	31,0	13,0
365	600	40,0	17,0
+/-4%	+/-5%	-15%	-15%

<b>Moisture</b>		8 %		
<b>Smoothness (PPS)</b>	top side	1,3	µm	ISO 8791
<b>Gloss (Hunter)</b>	top side	45	%	TAPPI T 480
<b>Brightness</b>	top side	87	%	ISO 2470, C/2°
<b>Cobb, g/m<sup>2</sup></b>	top side	40	g/m <sup>2</sup> (60s)	ISO 535
<b>Cobb, g/m<sup>2</sup></b>	reverse side	7	g/m <sup>2</sup> (30min)	ISO 535
<b>MVTR, g/m<sup>2</sup></b>		40	g/m <sup>2</sup>	75%, 25°C, 24h

Grease resistance tested with internal test methods, KIT>12.