

## Heritage

Uncoated folding box board



Grammage g/m <sup>2</sup>	Thickness µm	Stiffness, Taber (mN/m)	
		MD	CD
210	350	13,0	5,5
230	400	16,5	7,0
255	450	22,0	9,5
280	500	26,0	11,0
310	550	31,0	13,0
330	600	40,0	17,0
+/-4%	+/-5%	-15%	-15%

<b>Moisture</b>		8 %		+/- 1 %
<b>Cobb, g/m<sup>2</sup> (60s)</b>	top/reverse	50	g/m <sup>2</sup> (60s)	ISO 535
				max 60 g/m <sup>2</sup>

Hard sized grade on request (Cobb 180s < 50 g/m<sup>2</sup>)